

Grade: ARMC-1000

Manufacturer: Aremco Products, Inc.
Description: Ceramic and aluminum-filled, two-part, water-based paste.

PROPERTY	US VALUE		METRIC VALUE	
Type	Inorganic			
Filler	Aluminum			
Maximum Temperature	1400	°F	760	°C
Specific Gravity	1.8	gms/cc		
Viscosity	Paste	cps		
No. Components	2			
Mix Ratio	2:1			
Color	Light Grey			
Air Set	2-4	hours		
Heat Cure	160, 1-2	°F, hours	71, 1-2	°C, hours
Shelf Life	6	months		
Storage Temperature MIN	40	°F	4	°C
Storage Temperature MAX	90	°F	32	°C