

Grade: INTRS-ROPE

Manufacturer:

Graphtek LLC

Description:

Produced by twisting 3-plys of ceramic fiber wicking, this product is relatively soft and low in density.

PROPERTY	US VALUE		METRIC VALUE	
Color	Off-white			
Melting Point	3200	°F	1760	°C
Continuous Use Limit, up to	2300	°F	1260	°C
Insert Material	Glass			
Major Constituent	Silica(53%), Alumina(47%)			