

Grade: ARMC-617

Manufacturer:	Aremco Products, Inc.
Description:	One-part glass coating for producing hermetic seals in porous ceramics and refractories to 1450°F.

PROPERTY	US VALUE		METRIC VALUE	
Type	Glass			
Temperature	1450	°F	788	°C
Solids by Weight	57.0	%		
Application Temperature MIN	50	°F	10	°C
Application Temperature MAX	90	°F	32	°C
Drying Touch	.5	hours		
Drying Handling	.5	hours		
Drying Recoat	.5/1	Min/Max hours		
Min Air Set	1	hours		
Heat Cure	1830/.5	°F, hours	998/.5	°C, hours
Color	Clear			
No. Components	1			
Mixed Viscosity	1,100-1,500	@ 25°C, cps		
Specific Gravity	1.45	gms/cc		
VOC's	0.00	lbs/gal		
Shelf Life	6	months		
Storage Temperature	65	°F	18	°C