

Grade: ARMC-CP3015-GR

Manufacturer: Aremco Products, Inc.
Description: Grey-ceramic inorganic coating to 1400°F (760°C).

PROPERTY	US VALUE		METRIC VALUE	
Type	Inorganic			
Temperature Continuous	1400	°F	760	°C
Solids by Weight	44.5	%		
Solids by Volume	16.8	%		
WFT	6.00 (151.6)	mils (microns)		
DFT	1.0 (25.4)	mils (microns)		
Theoretical Dry Film Coverage	269	@ 1 mil, ft ² /gal	6.6	m ² /liter
Application Temperature MIN	50	°F	10	°C
Application Temperature MAX	90	°F	32	°C
Color	Gray			
No. Components	1			
Specific Gravity	1.38	gms/cc		
Shelf Life	6	months		
Min Air Set	1	hours		
Heat Cure	RT/24	°F, hours		°C, hours
Drying Touch	1-2	hours		
Drying Handling	2-4	hours		
Drying Recoat	1/24	Min/Max hours		