

## Grade: ARMC-CP3015-SS

**Manufacturer:** Aremco Products, Inc.  
**Description:** Stainless steel filled, inorganic coating to 1400°F (760°C).

PROPERTY	US VALUE		METRIC VALUE	
Type	<b>Inorganic</b>			
Temperature Continuous	<b>1400</b>	°F	<b>760</b>	°C
Solids by Weight	<b>42.3</b>	%		
Solids by Volume	<b>41.4</b>	%		
WFT	<b>2.42 (61.4)</b>	mils (microns)		
DFT	<b>1.0 (25.4)</b>	mils (microns)		
Theoretical Dry Film Coverage	<b>664</b>	@ 1 mil, ft <sup>2</sup> /gal	<b>16.3</b>	m <sup>2</sup> /liter
Application Temperature MIN	<b>50</b>	°F	<b>10</b>	°C
Application Temperature MAX	<b>90</b>	°F	<b>32</b>	°C
Color	<b>Stainless Steel</b>			
No. Components	<b>1</b>			
Specific Gravity	<b>1.47</b>	gms/cc		
Shelf Life	<b>6</b>	months		
Min Air Set	<b>1</b>	hours		
Heat Cure	<b>RT/24</b>	°F, hours		°C, hours
Drying Touch	<b>1-2</b>	hours		
Drying Handling	<b>2-4</b>	hours		
Drying Recoat	<b>1/24</b>	Min/Max hours		