

Grade: ARMC-CP3015-WH

Manufacturer: Aremco Products, Inc.
Description: White-ceramic inorganic coating to 1500°F (816°C).

PROPERTY	US VALUE		METRIC VALUE	
Type	Inorganic			
Temperature Continuous	1500	°F	816	°C
Solids by Weight	40.0	%		
Solids by Volume	20.6	%		
WFT	4.87 (123.6)	mils (microns)		
DFT	1.0 (25.4)	mils (microns)		
Theoretical Dry Film Coverage	330	@ 1 mil, ft ² /gal	8.1	m ² /liter
Application Temperature MIN	50	°F	10	°C
Application Temperature MAX	90	°F	32	°C
Color	White			
No. Components	1			
Specific Gravity	1.37	gms/cc		
Shelf Life	6	months		
Min Air Set	1	hours		
Heat Cure	RT/24	°F, hours		°C, hours
Drying Touch	1-2	hours		
Drying Handling	2-4	hours		
Drying Recoat	1/24	Min/Max hours		