

## Grade: ARMC-634-AS

**Manufacturer:** Aremco Products, Inc.  
**Description:** Alumina-silica based coating rated for continuous service temperatures up to 2300°F. For thin coating applications.

PROPERTY	US VALUE		METRIC VALUE	
Major Constituent	Alumina-Silica			
Maximum Temperature	2300	°F	1260	°C
Solids by Weight	61.2	%		
Solids by Volume	63.3	%		
Theoretical Coverage	1015	ft <sup>2</sup> / Gal @ 1 Mil DFT		
Specific Gravity	1.59	gms/cc		
Coating pH	7-8			
Viscosity	600-800	cps		
No. Components	1			
Color	Off White			
Shelf Life	6	months		
Storage Temperature MIN	40	°F	4	°C
Storage Temperature MAX	90	°F	32	°C
Thinner	634-AS-T			
Min Air Set	2	hours		
Heat Cure	200,2	°F, hours	93,2	°C, hours