

Grade: ARMC-634-AS-1

Manufacturer: Aremco Products, Inc.
Description: Alumina-silica based coating rated for continuous service temperatures up to 2300°F. For high build applications.

| PROPERTY | US VALUE | | METRIC VALUE | |
|-------------------------|----------------|-----------------------------------|--------------|-----------|
| Major Constituent | Alumina-Silica | | | |
| Maximum Temperature | 2300 | °F | 1260 | °C |
| Solids by Weight | 77.0 | % | | |
| Solids by Volume | 70.0 | % | | |
| Theoretical Coverage | 1120 | ft ² / Gal @ 1 Mil DFT | | |
| Specific Gravity | 1.70 | gms/cc | | |
| Coating pH | 7-8 | | | |
| Viscosity | 14,000 | cps | | |
| No. Components | 1 | | | |
| Color | White | | | |
| Shelf Life | 6 | months | | |
| Storage Temperature MIN | 40 | °F | 4 | °C |
| Storage Temperature MAX | 90 | °F | 32 | °C |
| Thinner | 634-AS1-T | | | |
| Min Air Set | 2 | hours | | |
| Heat Cure | 200,2 | °F, hours | 93,2 | °C, hours |