

Grade: GS-SP1

Manufacturer: Superior Graphite Co.

PROPERTY	US VALUE		METRIC VALUE	
Carrier	Solvent		Solvent	
Consistency	Thick		Thick	
Viscosity	>3,000	cps	>3,000	
Bulk Density	8.5-9.5	lb/gallon	1.01-1.14	g/cm ³
Flash Point	105	°F	41	°C
Dry Time (tack-free)	60-90 min @ 70°F		60-90 min @ 21°C	
Dry Time (complete)	90-120 min @ 70°F		90-120 min @ 21°C	
Average Application Coverage	200	ft ² /gallon	4.9	m ² /liter
Effective Temperature Range	-75° - 450°	°F	-59° - 232°	°C
Application Temperature MIN	50	°F	10	°C
Application Temperature MAX	100	°F	38	°C
Suggested Dilution Ratio	Not Recommended		Not Recommended	
Suggested Dilutant/Cleaner	Mineral Spirits or VM & P Naptha		Mineral Spirits or VM & P Naptha	
Shelf Life	24	months	24	