Grade: H35

Manufacturer: Helwig Carbon

PROPERTY	US VALUE		METRIC VALUE	
Type	Electrographite			
Resistivity	23	ohmXinX10 $^{-4}$		
Shore Hardness	50			
Strength	2500	psi	17	mpa
Voltage Drop	High			
Coefficient of Friction	Low			
Film #	2			
Rated Current	90	Amp/in ^{2}	14	Amp/cm ^{2}