

Manufacturer: Helwig Carbon

PROPERTY	US VALUE		METRIC VALUE	
Type	Electrographite			
Resistivity	23	ohmXinX10 ⁻⁴		
Shore Hardness	50			
Strength	2600	psi	17	mpa
Voltage Drop	Medium			
Coefficient of Friction	Low			
Film #	2			
Rated Current	100	Amp/in ²	15.5	Amp/cm ²