Grade: H619

Manufacturer: Helwig Carbon

K - 1 I I I I I I I I I I I I I I I I I I					
PROPERTY	US VALUE		METRIC VALUE		
Туре	Graphite				
Resistivity	19	ohmXinX10 ⁻⁴			
Shore Hardness	35				
Strength	4500	psi	31	mpa	
Voltage Drop	VH				
Coefficient of Friction	Low				
Film #	3				
Rated Current	50	Amp/in ²	7.8	Amp/cm ²	