

Grade: GR-62B

Manufacturer: Graphtek LLC

Method of Manufacturing: Compression Molded

Description: Superior strength, babbitt impregnated carbon-graphite

Property	US Value		Metric Value	
Density	0.087	lb/in ³	2.4	gr/cm ³
Tensile Strength	7500	psi	51.7	MPa
Compressive Strength	25000	psi	172.4	MPa
Hardness, Shore D	65			
CTE	3.0	in/in °F x 10 ⁻⁶		Microns/m °C
Application Temperature MAX	400	°F	204	°C