

Grade: EC-12

Manufacturer:	Tokai Carbon
Method of Manufacturing:	Isostatically Pressed
Description:	Multi-purpose fine grain isotropic graphite formulated for roughing and detailed EDMing
Comparable Grades:	AC-12

Property	US Value		Metric Value	
Density	0.0668	lb/in ³	1.85	gr/cm ³
Electrical Resistivity	0.00043	Ω·in		Ω·m
Flexural Strength	6700	psi	46.2	MPa
Shore Hardness	62			
Average Particle Size	0.00043	in	0.00109	cm