

Grade: EC-15

Manufacturer: Tokai Carbon
Method of Manufacturing: Isostatically Pressed
Description: Ultrafine grain isotropic graphite providing fine detailed EDMing while maintaining high tolerances. Excellent finish, high detail burns.
Comparable Grades: AC-15 POCO-200

Property	US Value		Metric Value	
Density	0.0658	lb/in ³	1.82	gr/cm ³
Electrical Resistivity	0.00049	Ω·in		Ω·m
Flexural Strength	9300	psi	64.1	MPa
Shore Hardness	66			
Average Particle Size	0.00028	in	0.00071	cm