

Grade: INTRS-GSS316

Manufacturer:	Graphtek LLC
Description:	Manufactured from flexible graphite foil adhesively bonded to a 0.002" (0.05mm) thick glued SUS316 stainless steel sheet insert.

PROPERTY	US VALUE		METRIC VALUE	
Density	0.036	lb/in ³	1	gr/cm ³
Ash	1	%	1	%
Temperature (Air)	842	°F	450	°C
Temperature (Inert)	1598	°F	870	°C
Compressibility	45	%	45	
Recovery	15	%	15	