

Grade: INTRS-GSSM316

Manufacturer: Graphtek LLC

Description: Manufactured from flexible graphite foil adhesively bonded to a 0.2 mm thick glued SUS316 stainless steel mesh insert.

PROPERTY	US VALUE		METRIC VALUE	
Density	0.036	lb/in ³	1	gr/cm ³
Ash	1	%	1	%
Temperature (Air)	842	°F	450	°C
Temperature (Inert)	1598	°F	870	°C
Compressibility	35	%	35	
Recovery	20	%	20	