

Manufacturer:

Graphtek LLC

Description:

Made from exfoliated graphite flake and is produced through an extensive calendaring process to give a thin flexible foil with no binder or resins.

PROPERTY	US VALUE		METRIC VALUE	
Density	0.040	lb/in ³	1.1	gr/cm ³
Ash	1	%	1	%
Temperature (Air)	1112	°F	600	°C
Temperature (Inert)	5972	°F	3300	°C
Compressibility	40	%	40	
Recovery	12	%	12	