

Grade: GR-CFL-Zero

Manufacturer:

Graphtek LLC

Description:

One side of the laminate has been purposely roughened to facilitate bonding to the surface. If bonding on both sides is required, the smooth side should be roughened up with sandpaper.

PROPERTY	US VALUE		METRIC VALUE	
Resin	Vinylester			
Fiber Type	33 m.s.i. Carbon			
Composite Type	Unidirectional Orientation			
Tensile Strength	390000	psi	2689.0	MPa
Flexural Strength	272000	psi	1875.4	MPa
Density	.054	lb/in ³	1.49	gr/cm ³